

Test Report No. AJFS1705002636FF Date: JUN.05, 2017 Page 1 of 6

#### SAVA

UL. ZYZNA 13M 42-200 CZESTOCHOWA

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: DÉCOR FR

Color: WHITE

**Composition: POLYESTER** 

**Country of Destination: POLAND** 

### **Test Requested:**

To determine the flammability (building materials class B1) in accordance with DIN 4102-1 (May 1998) Fire behaviour of building materials and elements Part 1: Classification of building materials, Requirements and testing

Test Results: -- See attached sheet -

Classification: The tested sample meets class B1 building materials requirements of DIN 4102-1 (May

1998).

### **Test Period:**

Sample Receiving Date : MAY.15, 2017

Test Performing Date : MAY.15, 2017 TO JUN.02, 2017

Signed for and on behalf of SGS-CSTC Co., Ltd. Anji Branch

Allen Zou Technical Manager





No. AJFS1705002636FF

Date: JUN.05, 2017

Page 2 of 6

### I. Test conducted

This test was conducted as per DIN 4102-15:1990 DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2, and Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials.

### II. Sample details

General description	DÉCOR FR
Color	White
Density	About 214 g/m <sup>2</sup>
Size of sample	1000mm×190mm & 190mm×90mm

## Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of  $23 \pm 2$  °C, and a relative humidity of  $50 \pm 6$  %.

#### III. Test results

## 1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: The front face

	Results of "Brandschacht" Test (part 1)								
Line		Unit	Test assemblies No.						
No.		Offic	Lengthwise	Widthwise					
1	Specimen fixings according to DIN 4102 part 15, table	/	1	1					
2	Max. flame height above lower sample edge;	cm	40	40					
3	Time 1)	min:s	0:26	0:30					
	Melting/burning through								
4	Time 1)	min:s	0:03	0:04					
	Back of specimen		/	/					
5	Flaming/glowing, Time 1)	min:s	0:05	0:05					
6	Discolouring, Time 1)	min:s	0:02	0:02					
	Burning droplets		/	/					
7	Begin 1)	min:s	0:09	0:10					
	Amount		/	/					
8	Specimen material falling off in separate droplets		/	/					
9	Specimen material falling off continuously		√	√					

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overlead, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.agx and, for electronic format documents ubject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.agx attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein Any holder of this document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits collent's instructions, if any. The Company's sole responsibility is to its Client and this document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or fastification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



No. AJFS1705002636FF

Date: JUN.05, 2017

Page 3 of 6

	Results of "Brandscha	acht" Tes	t (part 2)	
Line		Unit		mblies No.
No.		Offic	Lengthwise	Widthwise
	Burning parts		/	/
10	Begin 1)	min:s	0:06	0:07
11	Parts of sample falling off separately		√	$\checkmark$
12	Parts of sample falling off continuously		/	/
13	Duration of continued combustion on mesh base (max.)	min:s	No	No
	Burner flame impairment by dripping/falling material		No	No
14	Time 1)	min:s	/	/
	Premature ending of test			/
15	End of burning at specimen 1)	min:s	/	/
16	Time when test terminated (if applicable) 1)	min:s	/	/
	Burning after end of test		No	No
17	Duration	min:s	/	/
18	Number of specimens		/	/
19	Front of specimen	1	/	
20	Back of specimen		/	/
21	Height of flame	cm	/	/
	Glowing after end of test		No	No
22	Duration	min:s	/	/
23	Number of specimens		/	/
24	Front of specimen		/	/
25	Back of specimen		/	/
26	Top half of specimen		/	/
27	Bottom half of specimen		/	/

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sps.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sps.com/en/Terms-and-Conditions/T



No. AJFS1705002636FF

Date: JUN.05, 2017

Page 4 of 6

Results of "Brandschacht" Test (part 3)								
Line		Unit	Test assemblies No.					
No.	OI		Lengthwise		Widthwise			
	Residual length							
28	Single results	cm	60	62	62	60		
	- Single results	OIII	65	59	65	68		
29	Average of the single results	cm	61.5		63.8			
	Smoke temperature		/		/			
30	Max. of average	°C	142.7		140.6			
31	Time 1)	min:s	07:48		07:52			

Note: 1) time from start of testing

### Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

## 2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Flame application: 15s

### [ ✓ ] bottom edge ignition

Parameter	Lengthwise				Crosswise					
raidilletei		2	3	4	5	6	7	8	9	10
Whether or not flaming extinguished before reach the gauge mark(Yes/No)	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Whether or not flaming reach the measuring mark within 20 seconds(Yes/No)	No	No	No	No	No	No	No	No	No	No
Time for the flame tip to reach the gauge mark(s)	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA
Afterflame time (s)	0	0	0	0	0	0	0	0	0	0
Max. flame height (cm)	4	4	4	3	3	3	3	4	3	3
Molten dripping(Yes/No)	No	No	No	No	No	No	No	No	No	No
Smoke developments (visual impression)	Slight					Slight				

Note:

NA---Not applicable

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overlead, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.agx and, for electronic format documents ubject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.agx attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein Any holder of this document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits collent's instructions, if any. The Company's sole responsibility is to its Client and this document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or fastification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

1443, or email: CN. Doccheck@sg.s.com
No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejjang Province, China 313300 t (%6-572) 5018825 f (%6-572) 5018829 www.sgsgroup.com.cn
中国 • 浙江 • 安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (%6-572) 5018825 f (%6-572) 5018829 e sgs.china@sgs.com

<sup>\*</sup>Reduction in number of test (DIN 4102 Part 16, clause 5.2)



No. AJFS1705002636FF

Date: JUN.05, 2017

Page 5 of 6

#### IV. DIN 4102-1:1998 Criteria for classification

- 1) All materials, except flooring, may be classed as **B1** materials if they meet the following requirements a) and b):
- The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if
- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause
- 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- b) Pass DIN 4102-1: 1998 sub-clause 6.2.3 Ignitability Test if
  For each specimen, flaming doesn't reach the gage mark within 20s after flame application.
- 2) Materials may be classed as **B2** materials if they pass the ignitibility test specified in DIN 4102-1: 1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as B3 materials.

### **STATEMENTS:**

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

To be continued...



Unless otherwise agreed in writing, this document is itsued by the Company subject to its General Conditions of Service prints overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents overleaf, available on request of the control of the service of the control of the control



No. AJFS1705002636FF

Date: JUN.05, 2017

Page 6 of 6

**Photo Appendix:** 



SGS authenticate the photo on original report only

\*\*\* End of Report \*\*\*





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service prints overleaf, available on request or accessible at <a href="https://www.sgs.com/rierms-and-Conditions.aga,">https://www.sgs.com/rierms-and-Conditions.aga,</a> for electronic format document subject to Terms and Conditions for Electronic Documents at <a href="https://www.sgs.com/en/lerms-and-Conditions/Terms-en-Document-sep-Document-se